



Safety Grip tape data sheet

Subject	Result
Composition	PVC upper and PET base
Total applied thickness	1.19mm
Type of adhesive	Solvent acrylic
Overall thickness (mm)	1.3mm
Tackloop (kg/25.4mm)	6.23
Cohesion (minutes/25°C)	2812 ↑
Adhesion to steel (kg/25.4mm)	5.714
Temperature range	-40°C ~ +80°C
Maximum roll size	1346mmx100m
Life (months)	12 to 24

Coefficient of friction data

	Dry surface test result	Wet surface test result
H3415 Coarse resilient	95 TRL	60 TRL

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.